

10/012-766

PCT

WORLD INTELLECTUAL PRO
International

INTERNATIONAL APPLICATION PUBLISHED UNDER



(51) International Patent Classification ⁶ : D21F 11/00, D04H 1/46	A1	(11) WO 9606222A1
		(43) International Publication Date: 29 February 1996 (29.02.96)

(21) International Application Number: PCT/SE95/00938

(22) International Filing Date: 17 August 1995 (17.08.95)

(30) Priority Data:
9402804-0 22 August 1994 (22.08.94) SE(71) Applicant (for all designated States except US): MÖLNLYCKE
AB [SE/SE]; S-405 03 Göteborg (SE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): MILDING, Ebbe [SE/SE];
Granviksliden 8, S-435 35 Mölnlycke (SE). HOLM, Ulf
[SE/SE]; Engelbrektsgatan 63, 3 tr., S-412 52 Göteborg
(SE). LAMMERS, Gerhard [NL/NL]; De Zwette 32, NL-
9257 RP Noordbergum (NL).(74) Agents: GRAUDUMS, Valdis et al.; Albihn West AB, P.O.
Box 142, S-401 22 Göteborg (SE).(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH,
CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE,
KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MN,
MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK,
TJ, TM, TT, UA, UG, US, UZ, VN, European patent (AT,
BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL,
PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN,
ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD,
SZ, UG).**Published***With international search report.**Before the expiration of the time limit for amending the
claims and to be republished in the event of the receipt of
amendments.*(54) Title: NONWOVEN MATERIAL COMPRISING A CERTAIN PROPORTION OF RECYCLED FIBRES ORIGINATING FROM
NONWOVEN AND/OR TEXTILE WASTE

(57) Abstract

Nonwoven material produced by hydroentangling a fibre web, comprising recycled fibres with a fibre length of between 5 and 60 mm and a fineness of between 0.1 and 20 dtex, which are constituted by fibres which are mechanically freed from nonwoven waste, textile waste or the like, and which fibres are mixed with each other and possibly with new fibres in a wet-formed, foam-formed, air-laid or dry-laid fibre web which is hydroentangled with sufficient energy for forming a compact absorbent material.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LJ	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

5

Title: Nonwoven material comprising a certain proportion of recycled fibres originating from nonwoven and/or textile waste

10 Background to the invention:

The present invention relates to a nonwoven material produced by hydroentangling a fibre web.

15 Hydroentangling or spunlacing is a technique which was introduced in the 1970's, see e.g. CA patent No. 841,938. The method involves forming a fibre web, either dry-laid or wet-laid, whereafter the fibres are entangled, i.e. tangled together by means of very fine water-jets under high
20 pressure. A plurality of rows of water-jets are directed at the fibre web which is supported by a moving wire (mesh). The entangled fabric is then dried. The fibres which are used in the material can be constituted by staple fibres, e.g. polyester, rayon, nylon, polypropylene and the like,
25 by pulp fibres or by mixtures of pulp fibres and staple fibres. Spunlace materials can be produced cheaply and presents high absorption characteristics. Amongst other things they are used as drying materials for household or industrial use and as disposable materials within the field
30 of health-care etc.

Increased environmental awareness has led to the fact that a sparing use of our natural resources in the form of raw materials and sources of energy etc. is more and more often
35 viewed as being a matter of course. Recycling of paper fibres by collection of returned paper and textiles to charity collections has been known for a long time and is used commercially today for producing new products which function perfectly well.

40

Nonwoven waste of e.g. spunlace type can be recycled by melting it down into plastic granulate which can be used for production of new synthetic fibres. This presupposes that the waste is constituted by relatively "clean" synthetic material based on thermoplastic synthetic fibres. One example is recycling of polyester from bottles for producing polyester fibres which are used for carpet manufacture.

It is also known to mechanically shred nonwoven and textile waste and to use the freed recycled fibres. In this case, mixed waste comprising both synthetic and natural fibres can even be used. New materials for, for instance, sound insulation, filters and geotextiles can be produced from the recycled fibres by thermobinding, needling or adhesive binding.

A large portion of the production waste from nonwoven manufacture however presently goes to dumps as landfill or to waste incineration plants. Such production waste emanates from edge-trimming of the material webs, start-up waste and material which is discarded for various reasons. To the nonwoven waste is added used material as well as production waste.

Object and features of the invention

The object of the present invention is to achieve a nonwoven material with good absorption characteristics and good quality in other aspects, where recycled fibres of the aforementioned type are utilised. This has been solved by the invention in that the material comprises recycled fibres with a fibre length of between 5 and 60 mm and a fineness of between 0,1 and 20 dtex, and which are constituted by fibres which have been mechanically freed from nonwoven waste, textile waste or the like, which fibres are mixed with each other and possibly with new

fibres in a wet-formed, foam-formed, air-laid or dry-laid fibre web which is hydroentangled with sufficient energy for forming a compact absorbent material.

5 The recycled fibres can be constituted by synthetic fibres, plant fibres, regenerated cellulose fibres or pulp fibres.

By the addition of a suitable binder via impregnation, spraying, application of a coat or the like, certain properties such as wet strength and dry strength of the material can be additionally improved.

10 Description of the invention

The raw material fibre for the recycled fibres can be constituted partly by production waste in the form of edge-trimming waste, start-up waste and by other unused discarded material. It can also be constituted by other waste in the form of used fibre-based materials such as nonwoven and textiles (both woven and knitted). Such material may need to undergo certain cleaning stages, depending on the degree of contamination. The fibres can be recycled by mechanical shredding of the waste, whereby the material is cut into small bits which, with the help of spiked rollers, are torn up so that the fibres are freed. The waste in this case can be constituted by mixed materials, comprising not only natural fibres of different types, such as pulp fibres, cotton, jute, ramie etc. but also synthetic fibres, e.g. polyester, polypropylene, regenerated cellulose etc. The equipment for mechanical recycling of fibres from nonwoven and textile material is commercially available from many different machine suppliers.

30 The recycled fibres may possibly be mixed with fresh fibres, natural and/or synthetic, and formed into a fibre web which can be dry-laid, air-laid and carded, wet-formed

or foam-formed, i.e. the fibres are dispersed in a foamed liquid containing tenside and water, whereafter the fibre dispersion is dewatered on a wire (mesh). The proportion of the recycled fibres should be up to between 1 and 100 weight-%, preferably at least 5%. The fibre web thus formed is then subjected to hydroentangling with an energy input which suitably lies in the range of 400 to 800 kWh/ton. Hydroentangling can occur by conventional techniques and with equipment which is supplied by machine manufacturers. A preferred way of producing the material is by the method which is described in the Swedish patent application number 9402470-0, i.e. a foam-formed fibre web is hydroentangled directly following the forming. The advantage with foam-forming is that the freedom of choice of fibres is very large, such that longer fibres can be used with foam-forming than is the case with wet-forming. Additionally, foam-formed fibre webs present a high degree of uniformity in the fibre forming. However, as mentioned above, the fibre web can be formed in other ways than by foam-forming.

With the mechanical tearing of the waste material, the freeing of the fibres is often incomplete so that the recycled fibres can be present partly in the form of flocks. These flocks give non-uniformities in the produced material, which can have certain positive effects like the material having a more textile-like appearance and, in the case where the material is to be used as drying material, the cleaning capacity of the material is increased due to the mechanical friction effect which the non-uniformities produce. A negative effect is however that the non-uniformities in the material can cause reduced strength. For applications where strength is important, this can be increased by the addition of a suitable binder or wet-strengthener. Examples of such are polyamide-epichlorohydrin, EVA, butadiene-styrene, latex etc. The addition of binder can occur in a known manner by

impregnation, spraying, application of a layer or the like. A suitable amount of additive is between 0,1 and 10 weight-%, preferably between 1 and 5 weight-% calculated as part of the weight of the material.

- 5 The recycled fibres can be mixed with new fibres as mentioned above. For example a suitable method can be to utilise the production waste from one's own nonwoven production of e.g. spunlace material, by tearing up and freeing the fibres from such production waste and mixing in
10 a certain amount of recycled fibres into the raw material fibres. The advantage of this is that the composition of the recycled fibres and the other raw material fibres is the same, which ensures an even quality in the produced material. However, as previously mentioned, the recycled
15 fibres may be constituted by other nonwoven and textile waste and the produced material can be either wholly, or only partially, based on recycled fibres.

- The produced material is primarily intended as drying material for household purposes or for large consumers such
20 as workshops, industry, hospitals and other public institutions.

Example

- Several different materials with varying amounts of included recycled fibres were produced and tested, whereby
25 a comparison was made with a reference material produced from 100% new fibres. The new fibres were constituted by a mixture of 60% coniferous pulp + 40% synthetic fibres (PP + PET) 1.7dtex x 12 mm. The waste was constituted by mechanically recycled fibres from spunlace-nonwoven waste
30 comprising a mixture of pulp, polyester (1.7dtex x 12 mm) and rayon fibres (1.7 dtex x 6 mm). Fibre webs were produced by wet-forming or foam-forming and then

hydroentangling with about 600 kWh/ton, pressed lightly and dried by means of through-blowing. A wet-strengthener (B) of polyamide-epichlorohydrin type was added to certain of the materials in an amount corresponding to 2 weight-% dry substance calculated as part of the total weight of the material. The properties of the material are given in the following table.

Table 1

Property	Units	Method	100% New fibres	100 % Waste	50% Waste + 2% B (+48% New fibres)	25% Waste + 2% B (+ 73% New fibres)	98% New fibres + 2% B
Surface Weight	g/m ²	SCAN-P 6:75	80	83	79	86	85
Thickness	µm	SCAN P-47:83	420	490	400	420	450
Strength in tension, dry L	N/m	SCAN-P 38:80	1400	650	1450	1960	2320
Strength in tension, dry T	N/m	SCAN-P 38:80	650	460	540	930	760
Strength in tension, wet L	N/m	SCAN-P 58:86	660	250	640	950	1130
Strength in tension, wet T	N/m	SCAN-P 58:86	320	170	320	480	320
Water absorption, 5 secs.	g/g	SIS 25 12 28 *)	3.8	4.1	3.8	3.9	4.1
Water absorption, total	g/g	SIS 25 12 28 *)	4	4.1	3.8	4	4.1

It can be concluded that the material produced from 100% waste fibres without addition of binder presented notably lower strength than the reference material, whilst the absorption capability was totally in line with that of the reference material. With the addition of binder and with 50% mixing-in of waste fibres, a material was obtained which was equivalent to the reference material, whilst with a 25% mixing-in of the waste fibres, a material was obtained which was moreover better than the reference material in both dry and wet strength.

5

CLAIMS

1. Nonwoven material produced by hydroentangling a fibre web, characterized in that it comprises recycled fibres with a fibre length of between 5 and 60 mm and a fineness of between 0,1 and 20 dtex, which are constituted by fibres which have been mechanically freed from nonwoven waste, textile waste or the like, and which fibres are mixed with each other and possibly with new fibres in a wet-formed, foam-formed, air-laid or dry-laid fibre web which is hydroentangled with sufficient energy for forming a compact absorbent material.
2. Nonwoven material according to claim 1, characterized in that the recycled fibres are constituted by synthetic fibres, plant fibres, regenerated cellulose fibres and/or pulp fibres.
3. Nonwoven material according to claim 2, characterized in that a certain proportion of the recycled fibres are not completely freed, but form flocks which remain as non-uniformities in the material.
4. Nonwoven material according to any one, or any, of the preceding claims, characterized in that the certain proportion of the recycled fibres in the material is up to between 1 and 100%.
5. Nonwoven material according to any one, or any, of the preceding claims, characterized in that a wet-strengthener or a binder is added to the material by spraying, impregnation, coating with a layer or the like.

SUBSTITUTE SHEET

6. Nonwoven material according to claim 5, characterized in that the proportion of wet-strengthener or binder is up to between 0,1 to 10 weight-%, preferably between 1 and 5 weight-%.

5 7. Method of producing a nonwoven material according to claim 1, characterized in that a fibre web is formed by wet-forming, foam-forming, dry-forming or air-laying, said web comprising between 1 and 100 % recycled
10 fibres with a fibre length of between 5 and 60 mm and a fineness of between 0,1 and 20 dtex, which are constituted by fibres which have been freed by mechanical tearing of nonwoven waste, textile waste or the like, and forming a compact absorbent material of entangled fibres by
15 subjecting the fibre web to hydroentangling and thereafter drying the material.

8. Method according to claim 7, characterized in that the nonwoven waste is constituted by production waste and/or other nonwoven material or textile waste which is torn up and possible
20 mixed with new fibres before it is allowed to form said fibre web.

9. Method according to claim 7 or claim 8, characterized in that following hydroentangling, a wet-strengthener or binder is added to
25 the material by means of spraying, impregnation, coating with a layer or the like.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 95/00938

A. CLASSIFICATION OF SUBJECT MATTER

IPC6: D21F 11/00, D04H 1/46

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC6: D21F, D04H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

DIALOG: ALLSCIENCE

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4879170 A (FRED R. RADWANSKI ET AL), 7 November 1989 (07.11.89) --	1,7
A	US 4931355 A (FRED R. RADWANSKI ET AL), 5 June 1990 (05.06.90) -- -----	1,7

☐ Further documents are listed in the continuation of Box C. ☒ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

13 December 1995

Date of mailing of the international search report

15.12.1995

Name and mailing address of the ISA/
Swedish Patent Office
Box 5055, S-102 42 STOCKHOLM
Facsimile No. +46 8 666 02 86

Authorized officer

Olov Jensen
Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT
Information on patent family members

International application No.
PCT/SE 95/00938

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A- 4879170	07/11/89	AT-T- 107976	15/07/94
		AU-A- 3146689	21/09/89
		CA-A- 1278419	02/01/91
		DE-D, T- 68916455	02/02/95
		EP-A, A, A 0333209	20/09/89
		SE-T3- 0333209	
		ES-T- 2054908	16/08/94
		JP-A- 2014057	18/01/90
US-A- 4931355	05/06/90	AU-A- 3147489	21/09/89
		DE-U- 8916164	09/06/94
		DE-D, T- 68913057	09/06/94
		EP-A, A, A 0333228	20/09/89
		SE-T3- 0333228	
		ES-T- 2049268	16/04/94
		JP-A- 2026972	29/01/90